



## Ultra

### DESCRIPTION:

GemSeal® Ultra latex is an additive used with coal tar emulsion sealcoats to provide a tougher protective sealing film. Ultra should be used in all formulations containing sand to prevent aggregate rollout and increase life of film. Ultra Latex complies with all FAA specifications and ASTM specifications for coal tar sealcoats. Ultra latex additive is a milky blue latex containing proprietary surfacants and modifiers with a minimum solids content of 40%.

### FEATURES:

- Superior adhesion, crack resistance, fast setup and proper sand suspension
- Reduces Wet Track Abrasion Resistance (ASTM D3910) loss by more than 50%
- Non flammable

### APPLICATION:

The coal tar emulsion mix containing Ultra latex may be applied by conventional techniques. Allow minimum six hours drying time between coats on hot days. On cool or overcast poor drying condition days allow 24 hours between coats. Allow 24 hours curing between last coating and striping with latex paint. Consult with GemSeal recommended guidelines for complete information.

### COVERAGE:

Application rates for mixes containing Ultra latex shall range from 0.10 to 0.15 gallons per square yard.

### STORAGE:

Store in a cool, dry area. Avoid freezing. Product is no longer useful after freezing.

### CLEAN-UP:


Use soap and water if product is still in emulsion state. Dried latex will be difficult to remove from tools and equipment. Use GemSeal hand cleaner to remove residue from hands.

### INSTRUCTIONS FOR USE:

While agitating, slowly add mixing water to coal tar emulsion. Dilute Ultra latex with equal parts water and slowly add to diluted coal tar emulsion. When materials are completely mixed then slowly add the sand. Continue mixing until all ingredients are uniformly mixed.

### Recommended Mix Design Limits

GemSeal Coal Tar Emulsion (RP-355e)	100 gallons
Mix water	40-60 gallons
Ultra latex	2-5 gallons
Silica sand	400-600 pounds



**CAUTION:**

Remove from skin promptly. Keep out of reach of children. Use with adequate ventilation. Read label warnings and MSDS before using. Do not take internally. Harmful or fatal if swallowed. Induce vomiting with syrup of ipecac. Avoid prolonged contact with skin and breathing of vapor or spray mist. Flush skin with water immediately. In case of contact with eyes, flush with water for 15 minutes and get medical attention.

**MANUFACTURING & CUSTOMER SERVICE**

Atlanta, GA 404-696-7660 404-691-9049 - Fax	Boston, MA 508-791-6366 508-791-6339 - Fax	Dallas, TX 214-333-4343 214-333-4399 - Fax	Greensboro, NC 336-854-8200 336-854-8202 - Fax	Tampa, FL 813-623-3941 813-626-4103 - Fax
Baltimore, MD 410-238-3413 410-238-3414 - Fax	Chicago, IL 847-678-6220 847-678-2652 - Fax	Detroit, MI 734-753-4413 734-753-9033 - Fax	Memphis, TN 901-775-2585 901-755-2590 - Fax	



Corporate Headquarters:  
8201 Arrowridge Blvd. Charlotte, NC 28273

LIMITED 1 YEAR PRODUCT WARRANTY FROM DATE OF MANUFACTURE: Bonsal American warrants that this product and the materials used therein meet or exceed the applicable standards listed and enforced at the time of manufacture. Bonsal American will replace any product or part which proves defective due to quality of ingredients used or due to the manufacturing process itself. This Warranty shall apply only if the product is used in strict accordance with applicable specifications and instructions provided by Bonsal American for its use, and Bonsal American shall not be liable otherwise. Replacement of any defective product, or, at Bonsal American option, refund of the purchase of any defective product shall be the buyer's sole remedy under this Warranty, and Bonsal American shall in no event be liable for any damages in excess of the purchase price of the defective product. BONSAL AMERICAN SHALL IN NO EVENT BE LIABLE FOR ANY CONSEQUENTIAL, INCIDENTAL, OR SPECIAL DAMAGES.  
This Warranty constitutes the sole warranty given by Bonsal American in connection with this product, and Bonsal American has authorized no person to make or give any other warranties or representation, oral or written on its behalf. IN PARTICULAR, THERE ARE NO IMPLIED WARRANTIES, INCLUDING WITHOUT EXCEPTION WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. No modification of this Warranty in favor of any buyer shall be valid unless given in writing and signed by an officer of Bonsal American.