

## TARLOC® MPC PRIMER Primer for Coal Tar Emulsion Sealer

**DESCRIPTION:** Tarloc® MPC Primer is a pavement primer for oxidized, worn difficult to clean surfaces to improve bonding and wear of coal tar emulsion sealcoats.

### Unique Features:

- Primer for badly oxidized asphalt pavements prior to sealing.
- Primer for hard to clean areas, and polished aggregate conditions.
- Primer for concrete pavements prior to sealing.
- Oil spot sealer on both asphalt and concrete.
- Black-out paint for traffic/parking lines, etc.

### APPLICATION:

Tarloc® MPC can be applied by brush, squeegee, line paint sprayer or bulk truck spray-bar/hand wand. Since mild settling is possible, the product should be thoroughly stirred before application to the pavement. Stir to a uniform consistency. Apply Tarloc MPC in a thin film. Avoid over application. A wearing coat (s) of Latex modified sealer is then recommended over the Tarloc MPC Primer.

### APPLICATION RATE:

.025 to .050 gal./sq. yd.

#### For Asphalt Surfaces:

Mix 1 part Tarloc MPC with 1 part water.

#### For Concrete Surfaces:

Mix 1 part Tarloc MPC to 2 parts water.

### PHYSICAL PROPERTIES:

**APPEARANCE** Viscous, grey-green liquid

**SOLIDS** 30%

**VISCOSITY** 2,000 cPs

**DENSITY** 9.0 Lb./Gal.

**ODOR** Coal Tar

**DRIED FILM COLOR** Black

**DRYING TIME** 10 to 30 minutes (depending on surface conditions and thickness of application).

### PACKAGING:

Available in 5 gallon pails.

### STORAGE:

Store in a cool, dry area. Avoid freezing. Product is no longer useful after freezing.

**SPECIAL HANDLING:** Tarloc® MPC is slightly more irritable to the skin than regular pavement sealer. Protective clothing and skin creams should be used at all times.

### CAUTION:

**KEEP OUT OF REACH OF CHILDREN.**

Contains coal tar. Avoid prolonged contact with skin and breathing of vapor or spray mist. In case of contact with skin or eyes, flush with water immediately and get medical attention.

**DANGER:** Harmful if swallowed. If swallowed, do not induce vomiting. Call a physician immediately. **KEEP FROM FREEZING.**

### MANUFACTURING LOCATIONS

Baltimore, MD

(800) 495-9173

(410) 574-7882

Fax (410)-238-3414

Detroit, MI

(800) 495-9405

(734) 753-4413

Fax (734) 753-9033

Chicago, IL

(800) 491-7814

(847) 678-6220

Fax (847) 678-2652

Millbury, MA

(866) 246-9215

(508) 791-6366

Fax (508) 791-6339

### CORPORATE HEADQUARTERS

8201 Arrowridge Blvd./Charlotte, NC 28273

**WEBSITE:** [www.bonsalamerican.com](http://www.bonsalamerican.com)

Tarmax R-100® is the registered trademark of  
Southern Emulsions, Inc.